



STATE OF NORTH CAROLINA
DEPARTMENT OF TRANSPORTATION

BEVERLY EAVES PERDUE
GOVERNOR

EUGENE A. CONTI, JR.
SECRETARY

Materials and Test Unit
1801 Blue Ridge Road
Raleigh, NC 27607

June 13, 2012

Robert Antoinette
Powers Fasteners, Inc.
2 Powers Lane
Brewster, NY 10509

Dear Mr. Antoinette,

The Physical Testing Lab of the North Carolina Department of Transportation wishes to advise you that your Type 3A Epoxy, Pure50+ is acceptable for use. The test results are listed below. If you have any other questions or concerns, please let me know. Thanks.

Compressive Strength
1 day: 16020 psi
7 day: 20580 psi

Pot Life: 18 minutes

Sincerely,

A handwritten signature in black ink that reads "Dan Miller".

Dan Miller, EI
Assistant Physical Testing Engineer